Kav. DKI Blok 47 No.1, Meruya Utara, Jakarta Barat – 11620, INDONESIA. Tel: (62-21) 5854601 (Hunting) Fax: (62-21) 5854602 / 58908565



SMILE-FO-PR02-R&D-13

## Antack – 38

## **Anti-tack Liquid Agent**

Revision date: 22/04/2009

Antack - 38 is an anti-tack between surface of green compound, it can be used for most of rubber like, NR, SBR, BR, IIR, etc. Produces an excellent anti-tack effect and perfect surface appearance without any whitish or dusty in the rubber surface. Have a good emulsion stability, which cause no solution homogeneity-problem, no settling or floating problem. Has no effect in the building tack.

**Composition:** A combination of metal salt of fatty acids, and different non-ionic surfactants.

## **Properties:**

Physical Form: Liquid.

: White Translucent

Specific Gravity: + 1 gr/cc. Shelf Life : 1 year.

Application: Shake a little bit before use, Antack - 38 is applied by dipping the green compound into diluted Antack - 38. The dilution ratio by water is about 1:15-20 weight/weight, depend on the condition of the compound. The dilution rate some times should be adjusted with the nature of the Rubber compound.

**Packaging** : 100 Kg / Drum.

The information and recommendations contained herein are based upon data believed to be correct. However, no warranty is expressed or implied regarding the accuracy of this data or the results to be obtained from the use thereof. Health and safety precautions detailed in this data sheet may not be adequate for all individuals and/ or situations. It is the user's obligation to evaluate and use this data in order to comply with all applicable laws and regulations. It is the user's obligation to determine the suitability of use of the product for particular application.